

Esmalte sintético, exento de plomo, de gran dureza, excelente cubrición y fácil aplicación.

Sistema de pintado

En superficies pintadas en buen estado se puede pintar directamente, previo lavado y lijado suave. Si la pintura se encuentra en mal estado eliminar completamente.

En superficies de hierro, acero, aluminio y galvanizado limpiar e imprimir con **Imprimación Multisoporte (Cód. 2704-)**.

En superficies de madera, imprimir con **Selladora sintética Hangers (Cód. 21000)** en interior, y con **Fondo protector (Cód. 41200)** en exterior. Lijar entre mano y mano.

Aplicación

Con brocha, rodillo de esmaltar o pistola.

Producto al uso, no diluir, excepto en la aplicación a pistola, que se recomienda diluir con un 10-15% de **disolvente D-17. (Cód. 50004)**

Aplicar estirando bien la pintura, sin dejar más de 30-35 μ secas por capa. Espesores superiores pueden ocasionar problemas de arrugado, secado y repintado.

La temperatura de aplicación debe estar comprendida entre 5 y 30°C.

Aplicar como mínimo dos manos de esmalte.

Las características del acabado definitivo se alcanza transcurridos 7 días desde la aplicación.

Synthetic enamel, lead free, great hardness, excellent coverage and easy application.

Preparation

All surfaces to be painted should be clean, dry and free from loose and flaking material. Rub down previously painted surfaces with fine waterproof abrasive paper and rinse thoroughly. If necessary use **JUNO Paint stripper (Prod. Code 83100)**.

On iron, steel, aluminium and galvanized surfaces, clean and prime with **Multi-Support primer (Prod. Code 2704-)**.

On interior wood, prime with **JUNO Hangers synthetic sealer (Prod. Code 21000)**. For exterior, use **JUNO Undercoat Protector (Prod. Code 41200)**. Sand lightly between coats.

Application

Easy to apply by brush, roller or spray equipment.

Product is ready to use. Do not dilute, except for spray-gun application, where 10-15% dilution with **JUNO D-17 solvent (Prod. Code 50004)** is appropriate.

Apply with long paint strokes, leaving no more than 30-35 dry microns per coat. Thicker application can cause wrinkling, drying and repainting problems.

Application temperature must be between 5°C and 30°C.

Apply at least two coats. Total curing is reached in 7 days after final application.

JUNO

Barrio Saconi, 10
48950 Erandio (Vizcaya)
Spain

Tfno.: 944 670 062
Fax: 944 675 832
infoweb@juno.es
www.juno.es



JPV1 20 1018



JUNO PLUS

Esmalte sintético
brillante, satinado y mate

Synthetic enamel
Gloss, Satin and matt



JUNO

Brillante | Gloss



Blanco | White 16.000




Negro | Black 16.001

Satinado | Satin



Blanco | White 16.100




Negro | Black 16.101

Mate | Matt



Blanco | White 16.200



Negro | Black 16.201

4 LITROS		12 m ² /L			COV's 2010	IGNÍFUGO B-s1,d0
750 ml						
375 ml	USO *	RENDIMIENTO	DILUYENTE	APLICACIÓN	NORMA	FIRE RETARDANT

Esmalte Junoplus

Uso recomendado

Protección y decoración de superficies metálicas y de madera debidamente imprimadas. Los acabados brillante y satinado son válidos para interior y exterior, mientras que el acabado mate se recomienda solo para interior.

Acabado: Brillante, satinado o mate.

Secado (al tacto): 8 h. **Repintado:** 24 h (mín), 8 días (máx)

Diluyente: D-16 (cód. 50.012) o White Spirit.

Rendimiento teórico: 12 m²/l (35 µ secas).

Certificado reacción frente al fuego: B-s1,d0 (UNE 13501-1: 2007).

Junoplus enamel

Recommended use

For the protection and decoration of primed metal and wood. Ideal for use on Hardwood, Iron / Steel, Softwood, Timber, Window frames etc. Available in gloss and satin finishes for indoor and outdoor use, and matt finish for interior use.

Available finishes: Gloss, Satin and Matt

Touch Dry: 8 hours

Recoat: Min. 24 hours, Max. 8 days

Diluent: Use Juno D-16 (Prod. Code 50012) or White Spirit


Coverage (Theoretical): 12m²/l. (35 dry microns)

Fire Retardant Certification: B-s1,d0 (EN 13501-1:2007)


Brillante | Gloss



Gris claro | Light grey (RAL 7035) 16.031



Gris nube | Cloud grey (RAL 7001) 16.038



Gris oscuro | Dark grey (RAL 7031) 16.039



Gris tráfico | Traffic grey 16.006



Gamuza | Chamois 16.002



Ocre | Ocher 16.007



Pardo | Brown 16.003



Marrón arabia | Arabia brown 16.069



Verde hierba | Grass green 16.004



Verde prado | Meadow green (RAL 6001) 16.054



Verde musgo | Moss green (RAL 6005) 16.058



Verde carruajes | Dark green 16.011



Azul radiante | Bright blue (RAL 5017) 16.010



Azul ultramar | Overseas blue (RAL 5002) 16.009



Azul | Blue (RAL 5012) 16.008



Amarillo medio | Medium yellow (RAL 1028) 16.029



Marfil | Ivory 16.005




Rojo carruajes | Dark red (RAL 3005) 16.021




Rojo sangre | Blood red (RAL 3000) 16.022



Rojo fuego | Fire red (RAL 2002) 16.012




Azul ultramar | Overseas blue (RAL 5002) 16.109



Gris claro | Light grey (RAL 7035) 16.131




Amarillo medio | Medium yellow (RAL 1028) 16.129



Marrón arabia | Arabia brown 16.169




Rojo sangre | Blood red (RAL 3000) 16.122



Rojo carruajes | Dark red (RAL 3005) 16.121



Verde prado | Meadow green (RAL 6001) 16.154



Verde musgo | Moss green (RAL 6005) 16.158

Octubre 2018. Esta carta de colores anula las anteriores. Los colores y terminaciones representados pueden sufrir variaciones respecto a la aplicación real sobre el soporte.

October 2018. This colour card replaces and cancels any previous versions. Real applications may vary to colour and finish in this card once applied.

Satinado | Satin