

# Technical Datasheet

## Pavimyc Primer 2C Epoxy



Product Code: 48721 Flooring

### DESCRIPTION

Polyamide Epoxy-reinforcing primer providing excellent adhesion on non-porous surfaces.

### USE: INTERIOR

Recommended as a primer in epoxy systems to promote anchoring on concrete surfaces, tiles, stoneware, etc. Not suitable on bitumen content surfaces

### PROPERTIES

- Seals and consolidates concrete surfaces
- Improves adhesion for subsequent layers
- Guarantees a uniform finish
- Easy application

**Finish:** Semi-gloss

**Colour:** Transparent

**Mixture Viscosity:** Minimum 15" S/FR1002

**Mixture Density:** 0,98± 0,05 gr/cc S/FR1001

**Drying:** Touch Dry: 6-8 hours

**Repaintable max.:** 24 hours @ 20°C

**Repaintable max.:** Unlimited

**Diluent:** D-90

**Coverage:** 12 m<sup>2</sup>/l (25 dry microns)

**Mixture Solids in volume:** 37% ± 2 % Theoretical.

**Mixture Flash Point :** Flammable @ 27 °C

**Mixture ratio A/B in weight:** 2 : 1

**Mixture Ratio A/B in volume:** 2 : 1

**Mixture Pot life:** 8 hours

**Mixture Induction time:** 30 minutes

**VOC Content:** <600 g/l

48721 Clear



**Format:** 4L

The information contained in this data sheet may change and must be updated. Consult [www.junopaints.com](http://www.junopaints.com) or your nearest JUNO representative for the latest data sheet. The application technical advice, whether verbal, written or trial, is based on JUNO's experience and technical knowledge. The data displayed in this document should be considered a recommendation and as such does not imply any commitment, including with regard to possible industrial property rights of third parties. The application, the use and the transformation of the products supplied by JUNO are carried out by third parties. Consequently, the final result is the sole responsibility of the customer, applicator or handler of the products and not the supplying company. This document does not exempt the customer from conducting their own examination of the products supplied, in order to verify the suitability for the intended procedures and purposes. In the event of liability assumed by JUNO, it will be limited to the strict value of the merchandise supplied and used by the customer, whatever the damages caused. JUNO guarantees the quality of all its products, in accordance with the General Conditions of Sale in force.

# Technical Datasheet

## Pavimyc Primer 2C Epoxy



Product Code: 48721 Flooring

### SURFACE PREPARATION

**CONCRETE SURFACES.** Wait until completely set (min. 1 month). The surface must be completely dry. The humidity level of the pavement should not exceed 4%, measured at 2 cm depth. The surface must be firm and free of dust, grout, grease or any loose particles. Minimum tensile strength 15 kg/m<sup>2</sup>.

Remove grease and rubber stains with solvents or detergents, then rinse the detergent with water. Use blasting and milling if stains do not disappear.

Any slurry and curing agents should be removed by sandblasting and milling, and subsequently removing any dust, to obtain a textured surface free from foreign materials.

The surface to be painted must have a high enough adherence level to ensure proper adherence. It is advisable to carry out a prior test patch in the area to be painted (approx. 1m<sup>2</sup>) to check for the desired result.

### APPLICATION ADVICE

Stir the contents of the container until complete homogenization of the two components.

Apply on consistent, clean surfaces, free of efflorescence (saltpeter) and molds.

It is not advisable to apply the product on damp surfaces or excessively overheated by the sun.

Necessity of dilution depends on the porosity and condition of the surface to be painted.

**MIXTURE PREPARATION.** Stir component A in its tub and once homogenised add component B to it slowly, while stirring mechanically at low revolutions. Stir for 2 minutes until perfectly homogenized. If moving the mixed product into a different tub or holder, stir again to guarantee a mixture that is as homogeneous as possible. Do not use the product after 8 hours of mixing.

**ENVIRONMENTAL CONDITIONS.** During application and curing process the temperature should be maintained above 15°C.

The relative humidity should not exceed 70%. There should be no upward humidity. The temperature of the substrate should be at least 3°C above the dew point. Avoid condensation. Do not apply when risk of rain or strong wind is present.

**APPLICATION METHOD.** Brush or roller.

**CLEANING.** Clean working tools with JUNO D-90 Solvent (Prod.Code 50.010).

### SAFETY & ENVIRONMENT

When dealing with a solvent based product ensure good air ventilation and employ proper protection measures.

Avoid sources of ignition. Minimize product waste by estimating the real amount needed, taking into account the m<sup>2</sup>, porosity and texture of the substrate. Store surplus material in a ventilated, dry place. The container must be clean and of adequate size for the quantity of product left over.

Close containers carefully and keep them upright to prevent spills. Preserve containers from frost, high temperatures and direct exposure to the sun.

Store unused product for new use and to reduce environmental effects.

Do not eat, drink or smoke during the preparation and application of the product.

Surface preparation and application operations must be carried out with appropriate safety measures.

For more information consult the Material Safety Data Sheet.

In case of contact with eyes, rinse with plenty of clean water. Keep out of the reach of children.

Do not discharge into drains or the environment.

Dispose to an authorized waste collection point.

Consult your council about the correct recycling of both packaging and waste and leftover paint according to law and principles of environmental respect.